



BS 4772/ISO 2531

TYTON STYLE PUSH-ON FLEXIBLE JOINT TYPE



Standard K-9

Dimension in millimeters

Nominal Diameter D N	Thickness			Outside Diameter D E	Nominal Laying Length	Total Mass (kg)		
	e	e'				Pipe	Cement Mortar Lining	
		BS	ISO				BS	ISO
80	6.0	5	3	98	5000	64.5	14.0	8.5
100	6.1	5	3	118	5000	80.0	17.4	10.5
125	6.2	5	3	144	5000	100.0	22.2	13.5
150	6.3	5	3	170	5000	121.0	26.3	16.0
200	6.4	5	3	222	5000	163.0	35.3	21.0
250	6.8	5	3	274	5000	215.0	44.2	26.0
300	7.2	5	3	326	6000	323.0	63.6	37.8
350	7.7	5	5	378	6000	403.0	73.8	43.8
400	8.1	5	5	429	6000	482.0	84.0	50.0
450	8.6	5	5	480	6000	571.0	94.9	56.9
500	9.0	5	5	532	6000	669.0	105.0	63.0
600	9.9	5	5	635	6000	882.0	125.4	81.4
700	10.8	6	6	738	6000	1123.0	175.8	105.8
800	11.7	6	6	842	6000	1394.0	200.4	128.4
900	12.6	6	6	945	6000	1691.0	225.6	148.6
1000	13.5	6	6	1048	6000	2017.0	250.2	175.2
1100	14.4	6	6	1152	6000	2372.0	278.0	198.0
1200	15.3	6	6	1255	6000	2758.0	300.0	225.0
1400	17.1	9	9	1462	6000	3563.0	525.6	295.6
1500	18.0	9	9	1565	6000	4015.0	567.5	322.5
1600	18.9	9	9	1668	6000	4517.0	600.6	350.6
1800	20.7	9	9	1875	6000	5591.0	675.0	405.0
2000	22.5	9	9	2082	6000	6784.0	750.0	450.0